

GPDIGISERITX

DESCRIPTION	Heat melting powder glue for DIGISERI9541 system Textile	
TECHNICAL DATA	GPDIGISERITX is a heat melting powder glue with grain size 0-100 µm and great elasticity (copolyurethane).	
EQUIPMENT	Laser printer OKI Pro9541WT + Screen printing equipment + Oven + Heat press	
SUITABLE FOR	Use in combination with FCDIGISERITXF transfer film or FCDIGISERITXP transfer paper and WTDIGISERITX white screen-printing ink for printing natural or synthetic fabrics, in any colour.	

GPDIGISERITX is a heat melting powder glue which ensures **perfect compatibility with WTDIGISERITX white screen-printing ink** and high washing resistance and elasticity.

FEATURES

INSTRUCTIONS

The application of powder glue is the last step in the production of the DIGISERI9541 transfer.

Sprinkle the GPDIGISERITX* glue powder on the WTDIGISERITX white ink **immediately** after screen printing on the transfer, while it is still fresh.

Sprinkle with special equipment or by hand, using protective devices for eyes and respiratory tract. *Do not inhale.*

N.B.: It is advisable to sift the powder before use to avoid lumps.

1 *1 kg of powder glue covers 28-30 smq.

2 Dry in the oven at 160 °C-170 °C for 3-4 minutes.

3 Place the printed side of the transfer DIGISERI on the surface.

Press at 140 °C-150 °C for 10"-20" - medium pressure (4 bar).

4 Cold peel off. Press again with adhesive-proof tissue paper (AU CFC VELIN) for 10"-20".

WARNINGS

Printed fabrics can be machine washed **after 72 hours** at **40 °C**. Iron inside out or use protection. For more info contact your dealer.

Store in a cool and dry place.

Keep away from direct sun light.

Correct storage ensures 2 years shelf life.

STORAGE

The instructions on this sheet are merely indicative and contain details concerning tests carried out in our equipment. Do your own testing. The manufacturer will replace defective material but is not responsible for any damage resulting from incorrect use.

* Available cans: 0.5 Kg - 2 Kg.

SHOCKLINE
about your transfer paper

T. +39 0875 751194 - F. +39 0875 751329
info@shockline.it - skype shock.line
www.shockline.com

code